REST AVAILABLE COPY



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 4: A61K 49/00, 49/02, 49/04	A1	1	International Publication Number: International Publication Date:	4 July 1985 (04.07.85)
(21) International Application Number: PCT/SE (22) International Filing Date: 20 December 1984	(20.12. 830706 (21.12. Ulf (SE) ALFOF Id (SE) Box \$1 (Europout) SE (Europout) NL (Europout)	437 84) 60-7 83) SB SE/,).	Published With international search repo In English translation (filed in	nri. Swedish).
(54) Title: DIAGNOSTIC AND CONTRAST AC	GENT			

(57) Abstract

Spheres or particles in which a diagnostic or contrast agent for use in, for example, NMR technique, magnetometry, ultrasonics or radiology has been enclosed and in which the matrix is built up of carbohydrates, polyamino acids or synthetic polymers.

DIAGNOSTIC AND CONTRAST AGENT

BACKGROUND

The invention relates to response particles, preferably spheres, and their use as a diagnostic and contrast agent.

In diagnostic medicine, contrast agents are today being used primarily in X-ray diagnostics where an increased contrast effect is obtained during examination 10 of, for example, internal organs, such as the kidneys, the urinary tract, the digestive tract, the vascular system of the heart (angiography), etc. This contrast effect is based upon the fact that the contrast agent itself is less permeable to X-rays than the surrounding 15 tissue, as a result of which a different blackening of the X-ray plate is obtained.

X-raying implies certain radiation hazards, but during angiography the complication risk is associated in particular with the use of contrast agents.

In recent years, a number of new methods have been introduced in diagnostic radiology. One such method goes by the name NMR (Nuclear Magnetic Resonance) which provides information not only about the distribution of the water content in a specific tissue (in contradistinction 25 to radiology which merely gives a measure of the transmissibility of the X-rays in a specific tissue), but also about the chemical tissue structure which is different in normal and pathological tissue.

In the NMR method, a strong and homogeneous magnetic 30 field is applied across the tissue to be examined. By studying the so-called relaxation times of the protons of the molecules present, especially the protons of the water, it is possible to produce, via comprehensive and complex computer calculations, a visual image of the structure of the tissue concerned.

There is, however, an interest in being able to

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GA	Gebon	MIR	Mauritania
AU	Attralia	GB (United Kingdom	МW	Malawi
BB	Berbados	EU	Hungary	NL	Netherlands
BE	Belgium	ET.	Italy	NO	Norway
BG	Bulgaria	JP.	Japan	RO	Romania
BR	Brazil		Democratic People's Republic	SD	Studien
CF	Central African Republic		of Korsa	SE	Sweden
CG	Cango		Republic of Korsa	SN	Seneral
CH	Switzerland	Ц	Liechtenstein	SU	Soviet Union
CM	Cameroon	LE	Sri Lanks	110	Chad
DE	Germany, Federal Republic of	LU	Luxembours	TG	Togo
DK	Denmark	MC	Manaco	US	United States of Am
π	Piniand	MG	Madegascar		
FR	Frace	MIL	Mali		

WO 85/02772 PCT/SE84/00437

make a differential diagnosis between pieces of tissue having a high density of blood vessels and, alternatively, tissue having a low density of vessels. Such a situation which has considerable clinical interest, comprises the 5 localisation of tumours which, in their periphery, have a higher density of vessels as compared with normal tissue.

One useful method in the context is to inject into the vascular system some type of particles responsive 10 to a magnetic field and showing changes in the abovementioned relaxation times.

These magnetically responsive particles interfere with the above-mentioned homogeneous magnetic field in that there is formed, around each individual particle, 15 a field gradient which in its turn changes the relaxation times.

Put more simply, this means that "black holes" are formed around each particle which may be visualised and thus give an impression of the vessel density in the 20 tissue in question.

25

In another diagnostic method, use may be made of the movability of magnetically responsive particles in a tissue. The basic principle of this method may be studied according to the following: If magnetically responsive particle are introduced into a magnetic field, the particles will align themselves in the direction of the field lines. If the field is removed or shut down, the magnetically responsive particles will change their position in response to processes in the tissue. The duration of this change may, however, vary between different tissues and also in dependence upon the localisation of the particles within the tissue in question. This variability of the response of the magnetic material may be utilised diagnostically. If magnetically responsive 35 particles are administered to a patient, the distribution of the particles in different organs can be determined by means of a sensitive magnetometer capable of detecting

the above-mentioned changes (Nature (1983) 302, 336).

Ultrasonics is another visualisation technique in which sound-waves are reflected differently against different types of tissue, depending upon the acoustic 5 impedance of these tissues. Also in this respect, there is an interest in being able to use some type of contrast agent in order to obtain an amplification of specific organs. Particles of different types have here been shown to provide changed echo effects and a changed resolution associated therewith (J. Acoust.Soc.Am. (1983) 74, 1006).

It is also possible to use magnetically responsive particles having a Curie point of about 42°C for use at hyperthermia. In this instance, the magnetically respon-15 sive particles are retained during the treatment of the · hyperthermia by a magnetic field, but the moment the tissue temperature exceeds the Curie point, the particles disappear from the tissue because the magnetic responsiveness disappears at this temperature.

By labelling the particles with some gamma-radiating 20 nuclide (for example technetium-99m) it is possible to localise the particles by means of a gamma camera and thereby also to combine the examination with some of the other techniques referred to above.

When using particles within any of the abovementioned ranges, it is desired, in order to achieve optimal conditions, to be able to vary the amount of magnetically or otherwise responsive material, without affecting on that account the pharmacodynamic and cir-30 culatory characteristics of the particles. To be able to do this, one must use a technique which implies enclosing the responsive material in a matrix, preferably a matrix of spherical shape, and the matrix should per se satisfy the following criteria:

35 - biocompatible

25

- biologically degradable
- nonimmunogenic.

A matrix of this type normally is built up of some type of polymers which are held together by chemical bonds. Different types of polymers are available for making such matrices. However, the selection of polymers will be very limited if the above-mentioned criteria of the matrix are to be fulfilled.

One type of polymers that has proved useful in these contexts are the carbohydrates, especially those who are included in the body as a natural constituent.

Endogenous carbohydrates are represented by starch and glycogen, but also dextran may be included in this group because of its prolonged use as a blood substituent in medical service.

The production of a carbohydrate matrix satisfying 15 these criteria is described in PCT/SE82/00381, PCT/SE83/00106 and PCT/SE83/00268.

Another type of polymers that have proved to satisfy the said criteria are polyamino acids, such as proteins of the type albumin. The production of polyamino acid 20 matrices is disclosed in US-PS 4,247,406.

Further types of polymers are represented by synthetic polymers, such as acrylates, polystyrene etc. The production of matrices from synthetic polymers is well documented in literature.

It is in this connection extremely advantageous if covalent cross-linking of the polymers can be avoided in the production of a useful matrix. For example, covalently cross-linked carbohydrate matrices have been found to produce transformed cells, in the form of granuloma, when used on humans (Am.Surg. (1955) 142, 1045).

When using covalently cross-linked proteins, there is a risk of immunological reactions because the resulting derivatised protein is not recognised by the body's immunity system as a protein belonging to the body. There are, however, for specific systems no alternatives to the covalent cross-linking, especially when using synthetic polymers or combinations of different polymers and cross-

linking agents in order to obtain a useful system. As an example, it is possible to cross-link acrylic polymers with starch and, alternatively, to cross-link starch with acrylates.

Another useful possibility which is described in literature is the production of larger particles from smaller particles. For example, it is possible to produce, from 0.5 µm particles, conglomerates of larger particles, for example in the range of about 10 µm.

Another factor of importance to the injection of spheres into the vascular system is that the spheres have a size that prevents them from getting stuck in the capillary system of different tissues during the first passage. To prevent this, the particle must have a 15 diameter below 1 µm (Chem.Pharm.Bull. (1975) 23, 1452) and a surface structure of hydrophilic character.

When particles are injected into the vascular system, all particles will have collected after a given period of time in the liver or spleen (the RES system) 20 because the normal function of these organs is to purify the blood of foreign particles. At present, there is only one method described which is capable of collecting particles to organs other than those mentioned above, and this is by utilising magnetically responsive particles 25 or spheres.

This is of particular interest in the context of this invention because spheres containing magnetically responsive substances can be used and be made to stop in different tissues by means of the outer magnetic field. 30 When the magnetically responsive particles then are stuck in the desired tissue, the tissue in question can simply be visualised by means of the NMR method or some of the other techniques referred to above.

DESCRIPTION OF THE INVENTION

The invention relates to responsive particles, .35 preferably spheres, and their use as a diagnostic and

15

20

35

contrast agent. The invention shows that it is possible to utilise spheres as contrast agents, the responsive material being enclosed within a matrix. The responsive material may consist of, for example, magnetite particles enclosed in the form of discrete particles of varying size, or in the form of complexed ions.

One conceivable matrix for use in the context of this invention consists of carbohydrates that have been stabilised by crystallization, which means that the type of chemical bonds holding the polymeric network together is not covalent in character, mainly hydrogen bonds, van der Waals forces or, in some cases, ion bonds.

As carbohydrate, use may be made of all conceivable variants, including carbohydrates of varying molecular weight and/or substituted or otherwise derivatised carbohydrates. For example, it may be mentioned that it is possible to produce and use magnetically responsive carbohydrate particles in which the carbohydrate is of starch origin and low-molecular of the type glucose, maltose, dextrins etc., and successively increasing molecular weight up to native potato starch having a molecular weight of several millions. The same molecular weight range is applicable to other carbohydrate groups, such as dextran or glycogen.

25 Another matrix for use in the complex of this invention may consist of polyamino acids, such as the protein albumin in which the matrix is stabilised by heating and the cohering forces are not covalent in character, of the type hydrophobic interactions, hydrogen bonds, van der Waals forces or ion bonds. In a manner similar to what has been stated above, it is also possible to use synthetic polymers or combinations as matrix.

The following Example should not be regarded as restrictive and merely serves to illustrate the main features of the invention.

EXAMPLE

Dextran spheres having a size of about 1 μm with

enclosed magnetite particles (size 10-20 nm) were suspended in human serum. The relaxation times of the solution were measured with an NMR apparatus (Praxis II, Alnor Instrument AB, Nyköping) and compared with the relaxation times for the same serum without magnetically responsive dextran spheres. The following values of T1 and T2, respectively, were obtained.

				TI (ms)	TZ (ms)
	Serum without particles:		•	1660	400
10	Serum with particles: conc.:	0.05	mg/ml	1342	109
		0.1	mg/ml	1306	82.2
		0.2	mg/ml	1147	52.6
		0.5	mg/ml	968	30.7
		1.0	mg/ml	813	24.0
15	-	2.0	mg/ml	688	19.9
		4.0	mg/ml	691	22.9

CLAIMS

- 1. A sphere or particle for use in diagnostics or as a contrast agent, c h a r a c t e r i s e d in that it consists of a matrix and a diagnostic and/or contrast agent enclosed within said matrix.
- 2. A sphere or particle as claimed in claim 1, c h a r a c t e r i s e d in that the diagnostic or contrast agent is magnetically responsive.
- 3. A sphere or particle as claimed in claim 1, c h a r a c t e r i s e d in that the diagnostic or 10 contrast agent is X-ray impermeable.
 - 4. A sphere or particle as claimed in claim 1, c h a r a c t e r i s e d in that the diagnostic or contrast agent reflects sound waves.
- 5. A sphere or particle as claimed in claim 1, 15 characterised in that the contrast agent is a radioactive nuclide.
 - 6. A sphere or particle as claimed in one or more of claims 1-5, c h a r a c t e r i s e d in that the matrix has been stabilised by means of non-covalent bonds.
- 7. A sphere or particle as claimed in one or more of claims 1-6, c h a r a c t e r i s e d in that the matrix material consists of carbohydrates and their derivatives, polyamino acids or synthetic polymers.
- 8. A sphere or particle as claimed in claim 7,
 25 c h a r a c t e r i s e d in that the matrix, when it is a synthetic polymer, has been stabilised by means of covalent bonds.
 - 9. A sphere or particle as claimed in one or more of claims 1-8, c h a r a c t e r i s e d in that its diameter is in the range of 0.01-1000 µm, preferably below 1 µm.
 - 10. A sphere or particle as claimed in one or more of claims 1-9, c h a r a c t e r i s e d in that the particle per se has been built up of conglomerates of smaller particles or spheres.

INTERNATIONAL SEARCH REPORT

International Application No PCT/SE84/00437

I. CLASSIFICATION OF SUBJECT MATTEN (if several classification symbols apply, indicate all) * According to international Patent Classification (IPC) or to both National Classification and IPC 4				
A 61 K 49/00, 49/02, 49/04				
H. FIELD	S STARCHED			
		Minimum Docum	entation Searched ?	
Classificat	on System		Classification Symbols	
IPC 1		61 k 27/04, 27/08		
IPC 2		61 K 29/00,02, 43/00 61 K 43/00, 49/00,02	04 0434 24	, i
110)		Decumentation Searched other	then Minimum Documentation	
		te the Extent that such Decument	s ers included in the Fields Searched *	
SE, N	D, DK, FI	classes as above		<u>.</u>
IIL DOCK	IMENTS COME	IDERED TO BE RELEVANT		
Calegory *	Glietlen et	Decument, " with indication, where ex	propriets, of the relevant passages 12	Relevant to Claim No. 12
X	SE, B,	372 421 (MINNESOTA MI RING COMPANY) 23 December 1974	NING AND MANUFACTU-	1-10
X	SE, B,	7902009-5 (NEW ENGLAN 3 January 1984	D NUCLEAR CORP)	1-10
X	SE, B,	7407461-8 (PHARMACIA 19 October 1981 See claims, page 2-3	AB)	1-10
X	SE, 8,	7407462-6 (PHARMACIA 19 October 1981 See claims, page 2-3	AB)	1-10
X	SE, B,	7607673-6 (THE PROCTE 1 November 1982 See claims, page 3	R & GAMBLE COMPANY)	I-10 ·
x	EP, A2,	O 063 002 (RE SEARCH 2 October 1982 JP, 58013524 US, 4427646 AT, E, 11372	CORPORATION)	1-10
* Special	i categories of ell		"T" leter decument aublished offer the	o interpolice of the state
* Special categories of cited documents: 10 "T" later document oublished after the international filing date or shortly date and not in conflict with the application but considered to be a particular relevance to the confidence of the confidence				
invention				
RRING date - automate of particular restaurant to cannot be cannot				
which is citied to establish the publication date of enether citation or either assesses resear (as specified) "O" decument of sarticular relevance: the claimed invention cannot describe the citation or either assesses (as specified) "O" decument of sarticular relevance: the claimed invention cannot decument of sarticular relevance: the claimed invention to the cannot decument of sarticular relevances.				
A Annual taleutud ta eu alei electronal and estudicatu et containe te compliée mili elle di melle differ ench i				
ether means "P" desument published prior to the international filing date but "In the ert."				
	FICATION	earn etsiwee	"6" decument member of the same p	etent family
		on of the International Search	Dete of Mailing of this International Sec	erch Recent
400P 00 0 0			^*****	
	1985-03-13 ISBS -03- 26 International Searching Authority Signature of Authorized Offices			
_	-	•	Solvey Enlers	~
Swedis	h Patent (Office	Solveig Griksson	

FURTHE	R INFORMATION CONTINUED FROM THE SECOND SHEET
11	Fields searched (cont)
	National C1 30H:2/01, 10
	US C1 424:1, 1.1, 1.5
-	
	•
•	
1	
	BERVATIONS WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE 1
This inter	national search report has not been established in respect of certain dalms under Article 17(2) (s) for the following response in numbers because they relate to subject matter not required to be searched by this Authority, namely:
	•
2. Ctai men	n numbers
_	
	n numbers
VI. 0	SERVATIONS WHERE UNITY OF INVENTION IS LACKING 2
This inter	rational Searching Authority faund multiple inventions in this international application as follows:
1.□ A= 4	if required additional search less were timely paid by the applicant, this international search report covers all searchable cigims
	Internetural application.
thes	inly some of the required additional search fees were timely paid by the applicant, this international enacts report covers only a claims of the international application for which tees were paid, specifically claims:
•	
the i	retified additional aspect fees were timely paid by the applicant. Consequently, this informational eserch report le resideted to avention first mentioned in the clothe; it is covered by claim numbers:
	il scenthable claims aculd be searched without effort justifying an additional fee, the intermutional Searching Authority did not I payment of any additional los.
Romers of	
	edditional secret toos were accompanied by applicant's project. Indicat accompanied the payment of additional search (sec.

HIL DOCU	MENTS CONSIC	DERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEE	n
Calegory *	Citation o	f Cocument, with indication, where appropriets, of the relevant passages	Retevent to Claim No
x	us, A,	3 720 761 (WILLIAM W HUNTER) 13 March 1973 NL, 6915452 DE, 1951769 FR, 2020684 GB, 1255670 CA, 949880	1-10
x	WO, Al,	,78/00005 (KLAUS H MOSBACH) 7 December 1978 JP, 54017110 EP, 0007932 GB, 2035798 SE, 7706431 SE, 431214	1-10
x	WO, Al,	83/01738 (ULF SCHRÖDER & KLAUS MOSBACH) 26 May 1983 AU, 91274/82 EP, 0093757	1-10
	DE, Al,	2 744 493 (JOHN WYETH & BROTHER LTD) 13 April 1978 See claims, page 7-9 NL, 7710876 BE, 859291 FR, 2366835 LU, 78259 GB, 1548022 JP, 53044619 AU, 28825/77 CA, 1083042 AU, 513845 CH, 633717 US, 4371516 CA, 1097233 US, 4305502	1-10
A	WD, Al,	82/01006 (NATIONAL RESEARCH DEVELOPMENT CORPORATION) 1 April 1982	1-10
A	DE, C2,	2 336 546 (PHARMACIA AB) 31 January 1974	1-10
A	WO, Al,	82/00099 (KEY PHARMACEUTICALS INCORPORATED) 21 January 1982	1-10
P	WD, Al,	84/00294 (ULF SCHRÖDER) 2 February 1984	1-10
Р	CH, A5,	641 682 (FELIX DAENIKER) 15 March 1984	1-10

Form PCT/ISA/810 (estra sheet) (January 1985)

This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ BLACK BORDERS
☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
FADED TEXT OR DRAWING
☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
☐ SKEWED/SLANTED IMAGES
☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
☐ GRAY SCALE DOCUMENTS .
☐ LINES OR MARKS ON ORIGINAL DOCUMENT
☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
П отнер.

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.